MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made Explosive Materials Using the Matlab MicroCT Analysis GUI

I. M. Seetho, W. D. Brown, J. S. Kallman, H. E. Martz, W. T. White

October 6, 2011

Disclaimer

This document was prepared as an account of work sponsored by an agency of the United States government. Neither the United States government nor Lawrence Livermore National Security, LLC, nor any of their employees makes any warranty, expressed or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States government or Lawrence Livermore National Security, LLC. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States government or Lawrence Livermore National Security, LLC, and shall not be used for advertising or product endorsement purposes.

This work performed under the auspices of the U.S. Department of Energy by Lawrence Livermore National Laboratory under Contract DE-AC52-07NA27344.

<table>
<tr><td colspan="2">
Lawrence Livermore National Laboratory

Global Security Principal Directorate

Image Database Development Project
</td><td colspan="2">
</td></tr>
</table>

	STANDARD OPERATING PROCEDURE	
	Doc. No.	Rev. No.
	IDD-MCT-SOP-008	0

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made Explosive Materials Using the Matlab MicroCT Analysis GUI

Concurrence	Date
Technical Leader	
Approval	Date
IDD Project Principal Investigator	

Contents

For document control purposes, user SHALL ensure that all working copies are identical to the Official Use Copy posted at the designated ACEDPP project space on Livelink.

LLNL-TR-503292, Page 1 of 24

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

1.0   Purpose and Scope

This Standard Operating Procedure (SOP) provides the specific procedural steps for analyzing reconstructed CT images obtained under the IDD Standard Operating Procedures for data acquisition [1] and MicroCT image reconstruction [2], per the *IDD Quality Assurance Plan for MicroCT Scanning* [3]. Although intended to apply primarily to MicroCT data acquired in the HEAFCAT Facility at LLNL, these procedures may also be applied to data acquired at Tyndall from the YXLON cabinet and at TSL from the HEXCAT system. This SOP also provides the procedural steps for preparing the tables and graphs to be used in the reporting of analytical results. This SOP applies to R&D work – for production applications, use [4].

2.0   Precautions

There are no precautions from Integration Work Sheets or Facility Safety Plans and documents that are applicable to this work.

Work for this SOP is performed in project members' offices and does not present any high-risk safety situations. There are no operational safety boundaries such as set points or parameters that are applicable to this work.

3.0   Special Tools and Equipment

- Computer with Windows XP or above, with either Matlab version 2010a (or later) or the Matlab Compiler Runtime version 7.13 (or later) installed. Installations of Matlab require the inclusion of the image processing toolbox add-on.
- MicroCT GUI version 1.1.1 (for an outline of the files included in the GUI, see Appendix A). The Matlab-based MicroCT GUI includes a front-end graphical user interface (GUI) used for facilitating the reduction and statistical characterization of reconstructed CT image data, with add-on GUIs for viewing the resulting processed data and for comparing data across multiple tests for a form of similarity (see Appendix B). At each step in the data reduction process, this code writes resulting data to output files, which are outlined in section 5.2 of this SOP. The internal mathematical details of the software are discussed in Appendix C. Pre-use checks are outlined in Appendix D.
- Microsoft Excel 2007 (or later).
- *chart_macros.xlsm*. This macro-enabled Excel workbook is used to read in the output generated by the MicroCT GUI and generate plots of certain data.

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

4.0   Key Terms and Definitions

Experiment The acquisition of MicroCT data scanning a specimen with a specific x-ray source voltage (kV), with specific filtering medium and collimation parameters.

GUI Graphical User Interface

IDD Image Database Development Program

kV kilovolts (thousands of volts)

LAC Linear Attenuation Coefficient. A quantity characterizing how easily a material is penetrated by x-rays.

LMHU Livermore-Modified Hounsfield Unit – Hounsfield units shifted such that at 160kV with an aluminum and copper filter, water has a mean LAC value of 1000, and air has a value of 0.

MicroCT X-ray computed tomography using a system designed to scan small-quantity specimens.

QAP Quality Assurance Plan

QIP Quality Implementing Plan

Reference materials Six samples of known materials are used as comparison points to normalize and evaluate the quality of acquired specimen data values, in order to account for system and environment-generated variability.

SOP Standard Operating Procedure

Specimen The object to be x-rayed, consisting of a particular preparation of a sample of interest and the container holding the sample.

TAFRL/Tyndall Tyndall Air Force Base Research Lab

Test The collection of experiments scanning a particular preparation of specimen.

TSL Transportation Security Laboratory

$^{L}Z_{eff}$ Effective atomic number – an estimate of the average atomic number for a compound or mixture. The upper case L refers specifically to Livermore's method as given in [5].

μ The mean value of the LAC over a volume of interest for a given x-ray source voltage, filtration and collimation.

Note *Within this document, the adopted coordinate system is such that the x-axis is the horizontal axis in the slice image plane, the y-axis is the vertical axis in the slice image plane, and the z-axis traverses slices.*

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

5.0 Procedure

Notes *Assure applicable data and test dates are current and correct by comparing the dates provided in acquisition notes text file with the dates of scan and reconstruction files. The image files should have a filename structure "<specimen>_x.sdt" and "recobj_x.sdt" where **specimen** denotes the specimen name, and **x** is an integer value omitting leading zeros identifying the slice number of each scan file. The directory structure of the test directory will be outlined below in section 5.2.*

Stop the procedure immediately and notify the Technical Leader if there are any unusual discrepancies, failures, or abnormalities as noted within this document.

5.1 Preliminary Steps

This process begins when the Image Analyst is notified that data are available for processing and is given the location of the data to be analyzed. Note that these procedures apply only to the analysis of two-slit experiment data.

5.1.1 Verify the following:

5.1.1.1   The acquisition SOP has been followed (i.e. the data have been acquired with the dual-level carousel, the reference materials on the lower level of the carousel and the specimen(s) sitting on the upper level of the carousel, and every rotational view acquired includes either the reference materials or the specimen(s) in the field of view). This step should be completed in accordance with the directions outlined in the Data Acquisition and CT Reconstruction SOP documents.

5.1.1.2   The data has been acquired and reconstructed for at least the following two source-filtration and collimator settings:

    a.   160 kV AlCu, 2 slits, known as "Exp1"
    b.   100kV Al, 2 slits known as "Exp2"

5.1.1.3   If data has been acquired for the following optional source-filtration settings, it has also been reconstructed :

    c.   160kV Al, 2 slits, known as "Exp3"
    d.   300kV Cu or AlCu, 2 slits, known as "Exp4."
    e.   160kV AlCu, 1 slit, known as "Exp1 Open"
    f.   160kV Al, 1 slit, known as "Exp3 Open."

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

5.1.1.4   If files with mismatching dates are observed within an experiment set, stop work and notify the Technical Leader.

5.2   Data Analysis

5.2.1 Organize Data Files from Each Energy Spectrum

5.2.1.1   Copy all reconstruction files from each experiment of each test to be analyzed to the machine where it will be analyzed. For each experiment of each test present, both the image files (of the form *recobj_x.sdt*) and the corresponding settings files (of the form *recobj_x.spr*) should be present for every value of **x**, where **x** is an integer value formatted to exclude leading 0's. Both sets of files must be present for proper operation of the Automated MicroCT Analysis GUI (failure to meet this requirement may result in premature termination of the analysis process).

5.2.1.2   Organize the data into a standard directory layout as follows: The Matlab MicroCT segmentation graphical user interface (GUI) (version 1.1.1) requires that files be structured such that a test folder (the folder containing scan data of one material with references at all utilized energy levels and filtration settings) contains one subfolder for each experiment, in the format 'Exp**X**…' where **X** corresponds to the experiment number, identified above in section 5.1.1. Once organized the file structure should look like

..\Datapath\material_batchID_YYMMDD \

---Exp1
---Exp2

5.2.1.3   Currently, multiple separate test reconstructions cannot be analyzed from the same test directory. If multiple reconstructions of the same data, or multiple tests of the same specimen have been made, they should occupy different test directories.

For example, acquired data in the following layout should be separated into the canonical form shown in paragraph 2:

..\Datapath\material_batchID_YYMMDD\

---Exp1
---Exp1_b
---Exp2
---Exp2_b
A proper separation should result in the following:

..\Datapath\material _batch1_YYMMDD \

---Exp1
---Exp2
..\Datapath\material _batch2_YYMMDD \

---Exp1 (originally "Exp1_b")
---Exp2 (originally "Exp2_b")

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

Notes   *The original reconstruction image file indices have a jump in slice number between the specimen slices and the reference slices. This is a result of the physical separation between the two slits in the MicroCT array, where one slit allows illumination of the specimen and the other allows illumination of the references. The Matlab analysis script assumes that reconstruction files for specimen data have a slice number under 100, while reference reconstruction data have a slice number between 200 and 300, matching the output of the reconstruction step in the data analysis process, in order to make passing reconstruction step outputs to the analysis GUI as simple as possible.*

The data files are numbered with consecutive integers during the reconstruction process such that the first file name is of the form recobj_x .sdt and the nth data file name is of the form recobj_y.sdt, where y = x + n − 1. The accompanying .spr files should be numbered identically. Leading zeros are omitted. If the files in the dataset undergoing reduction are not numbered in this convention, stop work and notify the Technical Leader.

5.2.2 Run Data Analysis

5.2.2.1   Load the MicroCT GUI

If loading from source code:

To load the GUI, set Matlab's path to include the directory where micro_ct_GUI.m is located.

a. To add this folder to the path, within Matlab go to **File→Set Path…**
a. Within the Set Path GUI window, click on **Add Folder…**
b. Find the location of the MicroCT GUI files (this is left up to the user to store the software in a convenient location), select the folder and click **OK**.
c. Within the Set Path GUI window, click **Close**, and save changes if desired.
d. At the prompt, enter "micro_ct_GUI."

If loading from the executable:

Find the directory in which the executable "MicroCT.exe" sits, and double-click to execute (this is left up to the user to store the software in a convenient location).

5.2.2.2   Assign a destination directory.

For setting the destination directory, within the MicroCT GUI window click on the "Destination Directory" Browse button near the top of the window. This selection should be any directory where you would like the reduced data to be placed.

When placed locally, response time for the software package is faster, and thus data reduction will complete more quickly. For each test folder analyzed, the GUI will generate a new folder with the same name as the test folder within the destination directory. All reduced data will be saved within this new folder.

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

5.2.2.3   Using both the test plan directory browse and the single test browse functions, form a list of test folders to process.

In order for the GUI to accept a test directory for processing, Exp1 must be present, as this is used as a normalization reference (the procedure by which normalization is performed is outlined in Appendix A). Exp2 must also be present as the combination of high and low spectrum readings are used to compute effective atomic number. Exp3 and Exp4 are both optional scans, but will be analyzed automatically if present.

There are two ways to add a test folder to the processing list:

a. Setting a directory containing test folders by clicking the upper "Browse" button causes the GUI to search that folder for any directories that have a qualifying tree structure. The necessary qualification is the presence of Exp1 and Exp2, where both contain *recobj*.sdt* files in addition to corresponding *recobj*.spr* files.

Each valid test name will appear in the left-hand listbox. To add these to the processing list, select each individually within the listbox and click **Add**. Once added, a test name should appear within the right side listbox.

b. Alternatively, clicking the "Browse" button between the two listboxes will allow the user to select an individual test folder. This test folder will be checked to ensure it contains at least Exp1 and Exp2, and if so will be added to the queue.

If a test has been added that the user does not wish to process, that test may be selected in the "Data Reduction List" and removed by clicking **Remove**. At the current time, any test can only be represented once in the processing list.

5.2.2.4   Set parameters and run the data reduction.

There are three options provided (as radio button pairs) at the current time. The first identifies the presence of the square metal safety cage used at TSL for the software to remove with extra steps during image segmentation outlined in Appendix A of this document under "Segmentation." The second allows selection of the normalizing reference material. The third option allows the user to specify whether to perform a pre-erosion on the specimen voxels (such as if the specimen is in a Nalgene bottle versus being a solid rod).

The default values are:

a. no safety cage
b. water = 1000 LMHU at 160kV AlCu
c. specimen in a container.

Clicking on **Reset Defaults** changes any modified settings back to the default values. Default settings for all incoming additions can be set by clicking **Set Defaults** in the processing listbox, then applying the appropriate settings. All subsequent additions will match these settings. Settings can be individualized per test folder by clicking on the test folder in the processing list and using the radio buttons as desired.

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

Once the parameters are set, click **Run Data Reduction**. The reduction process will post a message that "data reduction for all materials is complete" upon completion (between 5–10 minutes per test on an Intel Xeon 2.67-GHz PC).

Notes   *The data reduction process saves reduced data in a file structure mirroring the input format: a folder is generated with the same name as the test folder within the destination directory; within this results folder, an experiment folder "Exp#" is generated for each present experiment. A summary .xls file is saved within the results folder, and data from each step in the reduction is saved within the corresponding experiment folders.*

There are two data formats for saved data during the data analysis process: Matlab-compatible .mat files, and ASCII text. The data files saved are:
a. Segmentation images (raw_material.mat)
b. Segmentation voxels (material.txt)
c. Cropped segmentation images (raw2_material.mat, no .txt equivalent)
d. Erosion images (erode_material.mat)
e. Erosion voxels (material_core.txt)
f. KDE values (kde_material.mat, no .txt equivalent)

ASCII text files are formatted with one line per voxel point. The ASCII line includes the x-position y-position z-position voxel-value, in that order. The x, y, and z positions are integer values while the voxels can be written in integer or floating-point format. All numeric values on each ASCII line are separated by spaces (data is space delimited). These files are structured to be compatible with Jeffrey S. Kallman's Java analysis codes (see [6]) and are not critical to the automated Matlab code analysis process.

Matlab files for saved images contain 3-dimensional arrays representing the collection of slices of images corresponding to the save file type. Each contains two arrays: an array of values, and a mask array. The arrays are oriented such that the first dimension represents the slice number.

5.3   Quality Assurance

5.3.1 QA Inspection of Images

5.3.1.1   Click on **Launch Viewer** within the micro_ct_GUI window to go over the segmented, eroded, overlayed images looking for any anomalies.

For each analysis run, the user should examine the resulting segmented images and erosions to determine that no qualitative errors have been made and the data quality is good. Conditions that should be noted include, but are not limited to:

a.   Erroneous segmentation or erosion
b.   The presence of visible streaks

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

    c.   Visible cupping or doming. If doming is observed, perform a lineout across the center of the object being observed, and note the approximate cup/dome-to-line value. If this value exceeds 10% of the mean LAC value of the entire object, notify the Technical Lead.

    d.   Mislabeling and mishandling of a reference (such as when they are not ordered properly in the carousel – see [7])

    e.   "Tuning fork" artifacts resulting from bad geometric information during reconstruction

    f.   Blurred Images

5.3.1.2   To view images from a test folder, within the micro_ct_viewer GUI window click on "Browse" and select the test folder.

Use the top pull-down menu to select the type of slice image. There are currently four types of images that micro_ct_viewer will display:

    a.   A segmented slice image that crops to include the segmented voxels plus 30 voxels in the image plane on all four sides.

    b.   An erosion slice image over the same field of view as the corresponding segmented image (to allow for comparison)

    c.   An overlay slice image which displays the erosion region relative to the entire segmentation region by dimming discarded voxels by a factor of ½.

    d.   Kernel density estimate plots

5.3.1.3   Use the second pull-down menu to select a material. Each of the references, as well as the test sample, can be selected.

Use the set of four push buttons to select the energy level and filtration settings. Only values corresponding to processed experiment values will be available for selection, the remaining push buttons will be inactive. Once all three selections are made, the appropriate list of slices will appear in the listbox. Select a slice to view its image.

While viewing a particular image type and material, clicking **Plot this Series** will generate a set of Matlab figures, one for each slice of the series.

View all sets of images and report any irregularities as described above in 5.3.1.1 to the technical lead.

5.4   Summarizing Results

5.4.1 Generate Excel Spreadsheet

5.4.1.1   The Matlab GUI generates an Excel file with the reduced data displayed in Sheet 1. Open up this file, *test_name_characterization.xls* and save as .xlsx. This is necessary because the **xlswrite** function in Matlab automatically generates an .xls file, while the .xlsx file format better supports additional used features (such as color coded cells).

5.4.1.2   Open up the chart macros spreadsheet *chart_macros.xlsm* and enable macros. Use the three chart macros ($^{\llcorner}$**Z$_{eff}$ vs μ$_{high}$**, **Low Range** $^{\llcorner}$**Z$_{eff}$ Fit**, and **High Range** $^{\llcorner}$**Z$_{eff}$ Fit**) to generate the appropriate plots. Format these plots as shown in the samples from the macros spreadsheet,

For document control purposes, user SHALL ensure that all working copies are identical to the Official Use Copy posted at the designated ACEDPP project space on Livelink.

LLNL-TR-503292, Page 9 of 24

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

replacing "specimen" with the appropriate name and date. The high-range fit R value can be computed using the **R_high** macro. The low-range fit R value is 1. The four macros are assigned to key combinations Ctrl-Shift-[Z,L,H,R]: Z for $^LZ_{eff}$ **vs** μ_{high}, L for **Low Range $^LZ_{eff}$ Fit**, H for **High Range $^LZ_{eff}$ Fit**, and R for **High Range Fit R-score**.

5.4.1.3   The kernel density estimates for the test sample at each scan energy are entered into Sheet 2, with each pair of data columns representing the experiments in numerical order (A:B for Exp1, F:G for Exp2, K:L for Exp3, P:Q for Exp4). To generate a plot of voxel distribution KDEs:

     a.   After selecting each pair of columns, within Excel click **Insert - Scatter - Scatter with Smooth Lines**.

     b.   Cut and paste each chart onto the next until they are merged into a single chart including all KDE curves . To do this, click to select a chart, push Ctrl-X to cut, click the next chart, and push Ctrl-V to paste. Continue this process until you have exactly one single aggregate KDE chart.

     c.   Right-click the chart, and select **Edit Data**.

     d.   Provide the appropriate labels for each of the KDE curves (match from among "160kV AlCu,"(exp1) "100kV Al,"(exp2) "160kV Al,"(exp3) "300kV Cu."(exp4)

     e.   Add a title and horizontal axis label matching the text style adopted in chart_macros.xlsm.

     f.   Copy the chart to the summary sheet (sheet 1). Generate another copy of the chart on the summary page as a semi-log plot to better emphasize the distribution tails. To convert to semi-log, right-click the vertical axis and select **Format Axis**. Select the **Logarithmic Scale** checkbox, set the minimum value to 1e-6, maximum value to 0.01, and "Horizontal axis crosses" value to 1e-6.

5.4.1.4   Change the name of the material in the "$^LZ_{eff}$ vs μ_{high}" plot on the summary page. The "Low Range $^LZ_{eff}$ Fit" and "High Range $^LZ_{eff}$ Fit" charts do not require the addition of the material name in the title.

Format the characterization spreadsheet using the "Summary" sheet of *chart_macros.xlsm* as a rough guideline.

5.4.1.5   Insert the appropriate images generated during the erosion process. From the MicroCT GUI window, click on **Launch Viewer**. From the viewer, select the test directory for which you are generating the current spreadsheet, and click **Generate Characterization Plots**. From each Matlab figure window, select **Edit→Copy Figure**, then paste the figure into the summary spreadsheet in the appropriate location.

5.4.1.6   Highlight certain data within the summary page according to the pattern observed in *chart_macros.xlsm*. Highlight the sample statistics and computed Z_{eff} on the summary page using green (from the Home tab within Excel). Highlight the water linear attenuation coefficient (LAC) at high energy with red.

5.4.2   Archive the Results on the Server

5.4.2.1   Create a subdirectory in a suitable location (for recent LLNL data acquisition that would be in the Analyses directory for the specimen, for TAFRL and TSL data acquisition that would be at the same level as the experiment subdirectories) with the name

For document control purposes, user SHALL ensure that all working copies are identical to the Official Use Copy
posted at the designated ACEDPP project space on Livelink.

LLNL-TR-503292, Page 10 of 24

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

a#a#_miscID_acqdate_analysis**_INIT_date**

where **a#a#** is the specimen name, **acqdate** is the date of data acquisition in the form yymmdd, **miscID** is any other identifying information that might be available (such as batch number, set number if there were multiple data sets taken in a day, etc), **INIT** are the initials of the person who analyzed the data, and **date** is the date the analysis took place.

5.4.2.2   Copy everything generated during the analysis (including the directory structure and Excel spreadsheets) into this subdirectory. Refer to the IDD Records Management QIP [8] for responsibilities in the handling of generated data.

5.5   Post-Procedure Checks and Notifications

5.5.1.1   Notify the IDD Records Librarian that the data are available for archival. Copy the IDD Technical Leads, PI, and Deputy Project Leader on the notification.

5.5.1.2   Contact the team member responsible for writing of reports once analyzed data are available on the server.

6.0   Records

Analysis results generated from this SOP shall be managed per the IDD *Document Management* QIP [9] and the *IDD Project Data Management Plan* [10].

7.0   Review Interval

This SOP shall be called for periodic review at an interval not to exceed 1 year from its previous issue.

8.0   Document Revision History

Date	Revision	Author	Responsible Manager	Comments
12/15/2010	0	Isaac Seetho	Harry Martz	
1/13/2011	0	Isaac Seetho	Harry Martz	Edit addressing various comments
3/22/2011	0	Isaac Seetho	Harry Martz	Edit addressing various comments
9/23/2011	0	Isaac Seetho	Harry Martz	Edit addressing various comments
10/4/2011	0	Isaac Seetho	Harry Martz	Edit addressing comments

9.0   References

1. *MicroCT: Acquisition of CT Data of Home Made Explosive Matierials*, IDD Standard Operating Procedure, IDD-MCT-SOP-003, latest revision.
2. *MicroCT: Reconstructing X-ray Computerized Tomographic Images from Data Acquired on LLNL MicroCT Systems*, IDD Standard Operating Procedure, IDD-MCT-SOP-004, latest revision.
3. Lawrence Livermore National Laboratory, *IDD Quality Assurance Plan for MicroCT Scanning*, IDD-MCT-QAP, latest revision, LLNL-AM-463479.

For document control purposes, user SHALL ensure that all working copies are identical to the Official Use Copy posted at the designated ACEDPP project space on Livelink.

LLNL-TR-503292, Page 11 of 24

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

4. *MicroCT: Automated Analysis of CT Reconstructed Data of Home Made Explosive Materials Using the Matlab MicroCT Analysis GUI*, IDD Standard Operating Procedure, IDD-MCT-SOP-007, latest revision.

5. Jeffrey S. Kallman, Daniel J. Schneberk, Harry E. Martz, Jr., *Two-energy Ratio Method to Determine Zeff from Reference Materials: A Comparison of an Explosive and a Simulant*, Version 3, Lawrence Livermore National Laboratory, LLNL-TR-491153, June 24, 2011.

6. *MicroCT: Analysis of CT Reconstructed Data of Home Made Explosive Materials*, IDD Standard Operating Procedure, IDD-MCT-SOP-002, latest revision.

7. Jerel A. Smith, Daniel J. Schneberk, Jeffrey S. Kallman, Harry E. Martz, Jr., David Hoey, *Documentation of the LLNL and Tyndall Micro-Computed-Tomography Systems*, Version 091216, Lawrence Livermore National Laboratory, LLNL-TR-421377, December 17, 2009.

8. *Records Management*, IDD Quality Implementing Procedure, IDD-QIP-002, latest revision.

9. *Document Management*, IDD Quality Implementing Procedure, IDD-QIP-001, latest revision.

10. *IDD Data Management Plan*, IDD-DAMA-Plan, latest revision.

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

Appendix A: Semi-Automated MicroCT Analysis GUI File Structure

In **source code** form, the Automated MicroCT Analysis GUI contains three types of Matlab files:

- **GUIDE Figure Files** (*micro_ct_gui_dlg.fig, kde_comp_dlg,fig, micro_ct_viewer_dlg.fig*)

  These files are automatically generated by the GUIDE GUI development toolbox within Matlab. These files specify graphical user interface layout and assign labels and types to all GUI elements. One file is required for each corresponding GUI window.

- **Dialog Box Control Files** (*micro_ct_gui_dlg.m, kde_comp_dlg.m, micro_ct_viewer_dlg.m*)

  These files are used to specify GUI functionality, by supplying code connecting each GUI element with the corresponding callback functions.

- **Function Definition Files** (*micro_ct_GUI.m, kde_comp.m, micro_ct_viewer.m*)

  These files contain functional definitions for all Matlab callback functions, as well as define the state variables stored by the corresponding GUIs.

In **executable** form, the Automated MicroCT Analysis GUI contains the following files:

- ***MicroCT.exe***

  This is the main executable which will run the Automated MicroCT Analysis GUI.

In addition, **both** versions of the analysis software contain the following files:

- ***chart_macros.xls***

  This is an Excel file containing macros used in the generation of the results Excel spreadsheet for each test material analyzed by the Automated MicroCT Analysis GUI.

For document control purposes, user SHALL ensure that all working copies are identical to the Official Use Copy
posted at the designated ACEDPP project space on Livelink.

LLNL-TR-503292, Page 13 of 24

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

Appendix B: GUI Operation and Capabilities

Figure 1. Initial graphical user interface of the Automated MicroCT Analysis program.

Main Automated MicroCT Analysis GUI Window

The main window of the Automated MicroCT Analysis GUI has the following fields and functions:

- **Browse Test Plan Directory.** Clicking on this Browse button will bring up a browse window allowing the user to set a directory to scan for viable test folders. Any viable test folders found in this directory will be listed in the Test Plan Listbox in the lower left of the GUI window. Candidate test folders are checked against the layout requirements identified in section 5.2.1 of this document. Alternatively, the user can edit the text in the accompanying edit box manually. Any manually entered directory will be checked for existence. If the directory does not exist, the edit box will revert to its last valid value (includes the empty string).

- **Browse Destination Directory.** Clicking on this Browse button will bring up a browse window allowing the user to set the destination directory for save data. The program generates a new subdirectory within the destination directory for each test reduced, and saves files in the format identified in section 5.2.2 of this document. Alternatively, the user can edit the text in the accompanying edit box manually. Any manually entered directory will be checked for existence. If

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

the directory does not exist, the edit box will revert to its last valid value (includes the empty string).

- **Current Test and Operation Listing.** This text box cannot be edited, and will display the current step of the data reduction process as it proceeds.
- **Indicate TSL "Square Enclosure" Dataset Radio Buttons.** These buttons are used to toggle for the presence of a TSL square container around the outside of the specimen container. The differing treatment of TSL containers in the segmentation and erosion process is outlined in the MicroCT GUI Mathematical Description Document. To set this setting, select the candidate test in the Data Reduction Listbox, then select the desired radio button.
- **Normalization Reference Selection Radio Buttons.** These buttons are used to select the normalization medium, either water (set to equal 1000 for Exp1), or Delrin (set to equal 1400 for Exp1). To set this setting, select the candidate test in the Data Reduction Listbox, then select the desired radio button.
- **Container Toggle Radio Buttons.** These radio buttons can be used to toggle for the presence of a container, in the case where a solid material is being scanned (such as a metal rod with no container). This option has the effect of modifying the erosion process applied to the specimen sample, as discussed in the MicroCT GUI Mathematical Description Document. To set this setting, select the candidate test in the Data Reduction Listbox, then select the desired radio button.
- **Test Plan Listbox.** If the user specifies a Test Plan Directory, any valid test folders found in the directory will be displayed in this listbox.
- **Data Reduction Listbox.** If the user has added tests to be run through the data reduction process, they will be displayed in this listbox.
- **Add From Test Plan Listbox.** Clicking on a test in the Test Plan Listbox, and then clicking the **Add** button will add the selected test to the Data Reduction Listbox.
- **Remove From Data Reduction Listbox.** Clicking on a test in the Data Reduction Listbox, and then clicking the **Remove** button will remove the selected test from the Data Reduction Listbox.
- **Browse for Test Data Folder.** Clicking on this Browse button will bring up a browse window allowing you to specify a test folder to add to the Data Reduction Listbox. Any folder selected will be checked for a directory structure matching that specified in section 5.2.1 of this document.
- **Launch Viewer.** Clicking on this button launches a separate Viewer GUI window.
- **Launch Similarity Computation GUI.** Clicking on this button launches a separate Similarity GUI window.
- **Run Data Reduction on Data Reduction List.** Clicking on this button starts the data reduction process on the members of the Data Reduction Listbox. Note that the user must have: specified a destination directory; found the location of *watertosnake.jar*; specified a nonempty data reduction list in order for the Run Data Reduction button to become active.

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

Figure 2. The dialog box that appears whenever a Browse button is selected

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

Figure 3. The Automated MicroCT Analysis Program Viewer GUI.

Automated MicroCT Analysis GUI Viewer Window

The viewer window of the Automated MicroCT Analysis GUI has the following fields and controls:

- **Browse for Test Results Directory.** Clicking on this Browse Directory button will bring up a browse window allowing the user to specify the test results directory from which to display slice images. Alternatively, the user can edit the text in the accompanying edit box manually. Any entered directory will be checked for existence, as well as existence of data reduction results files generated by the GUI and which should be structured within the directory according to the format specified in section 5.2.2 of this document. If no such files are found, the edit box will revert to its last valid value (includes the empty string).

- **Select Image Type.** Clicking on this pulldown menu when a valid results directory is specified allows the user to select from one of several different types of images to view:

  o Segmentation Images. Displays, for each slice, the voxels resulting from the segmentation process.

  o Erosion Images. Displays, for each slice, the voxels resulting from the erosion process.

  o Kernel Density Estimates. Displays, for each material and spectrum combination, a Kernel Density Estimate (KDE) of the erosion voxels for that material at that energy value. The process by which this KDE is obtained is described in Appendix C of this document.

For document control purposes, user SHALL ensure that all working copies are identical to the Official Use Copy
posted at the designated ACEDPP project space on Livelink.

LLNL-TR-503292, Page 17 of 24

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

o **Overlay Images.** Displays, for each slice, the voxels from the erosion image scaled by a factor of 1, and the remaining voxels of the segmentation image scaled by a factor of 0.5. The boundary of the erosion voxels is marked by a white line. In images containing a container, a white circle marks the estimated container boundary.

For each of these images, the colormap is gray, and set such that the maximum voxel value corresponds to white, while the minimum voxel value corresponds to black.

- **Select Material.** Clicking on this pulldown menu when a valid results directory is specified allows the user to select the material for which images should be displayed. Aluminum, Delrin, Ethanol, Graphite, Teflon and Water identify the corresponding reference materials. specimen refers specifically to the main test sample (in some cases this may be the same material as one of the references).

- **Select Spectrum.** Only one of these buttons is active at any given time, and the toggle button selected (it should appear to be depressed in the GUI window) determines the spectrum value for which images will be displayed. The labels correspond to spectrum and filtering combinations specified in subsection 5.1 of this document.

- **Select Slice.** When an image type (excluding KDE), material, and spectrum value are selected, the listbox on the right side of the GUI will be populated with the slices corresponding to the selections. Clicking on one of these frames to select it within the listbox will plot the frame in the space on the left side of the GUI.

- **Generate Characterization Plots.** Selecting this option will generate all plots used in the writing of MicroCT reports. These include segmentation area plots, erosion area plots, overlay area plots, and plots of the differential of the erosion area (taken by the absolute value of subtracting each erosion voxel from the voxel to the right), for the specimen only, at all available spectra.

- **Plot Current Series.** Selecting this option will generate an individual Matlab figure window for each image slice listed in the listbox on the right side of the GUI, and plot each slice in the corresponding figure window.

- **Close Plots.** Selecting this option will close all open figure windows associated with the Automated MicroCT Analysis GUI.

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

Figure 4. Similarity Computation GUI Window.

Similarity Computation GUI Window

The similarity computation window of the Automated MicroCT Analysis GUI has the following fields and controls:

- **Browse Test Plan Directory (Data Reduction Results).** Clicking on this Browse button will bring up a browse window allowing the user to set a directory to scan for viable test folders. Any viable test folders found in this directory will be listed in the Test Plan Listbox in the lower left of the GUI window. Candidate test folders are checked against the layout requirements identified in section 5.2.2 of this document. Alternatively, the user can edit the text in the accompanying edit box manually. Any manually entered directory will be checked for existence. If the directory does not exist, the edit box will revert to its last valid value (includes the empty string).
- **Browse Destination Directory (KDE Results).** Clicking on this Browse button will bring up a browse window allowing the user to set the destination directory for save data. The program saves files in the .mat (Matlab) and .xls (Microsoft Excel) formats. Alternatively, the user can edit the text in the accompanying edit box manually. Any manually entered directory will be checked for existence. If the directory does not exist, the edit box will revert to its last valid value (includes the empty string).
- **Test Plan Listbox.** If the user specifies a Test Plan Directory, any valid test folders found in the directory will be displayed in this listbox.

For document control purposes, user SHALL ensure that all working copies are identical to the Official Use Copy
posted at the designated ACEDPP project space on Livelink.

LLNL-TR-503292, Page 19 of 24

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

- **Similarity Comparison Listbox.** If the user has added tests to be run through the data reduction process, they will be displayed in this listbox.

- **Add From Test Plan Listbox.** Clicking on a test in the Test Plan Listbox, and then clicking the **Add** button will add the selected test to the Similarity Comparison Listbox.

- **Remove From Similarity Comparison Listbox.** Clicking on a test in the Similarity Comparison Listbox, and then clicking the **Remove** button will remove the selected test from the Similarity Comparison Listbox.

- **Browse for Test Data Folder.** Clicking on this Browse button will bring up a browse window allowing you to specify a test folder to add to the Similarity Comparison Listbox. Any folder selected will be checked for a directory structure matching that specified in section 5.2.1 of this document.

- **Run Similarity Comparison.** Clicking on this button will start the similarity comparison process. The similarity comparison process will generate an Excel file in the destination directory containing similarity tables, with one sheet for each spectrum present. Similarity values are computed using the KDE distributions from each material at each spectrum. Similarity comparison requires:

  - The same material is being compared against itself
  - The two materials are scanned using the same spectrum
  - The two KDEs are obtained using data normalized to the same reference at the same spectrum.

Similarity is computed by summing up the minima of two KDEs over the same domain set, multiplied by the granularity of the domain set. The domain set occupies the X-axis while the corresponding KDE values occupy the Y-axis.

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

Appendix C: MicroCT Data Reduction Algorithm Overview

The MicroCT Matlab GUI breaks data analysis down into four main steps, as identified below.

1. Segmentation

For each energy spectrum, the Matlab software generates a list of *recobj*.sdt* reconstruction files, and partitions these files into two categories, specimen and reference, according to the file number (under 200 for specimen and between 200 and 300 for references). Within each subset, the first slice and last two slices are disregarded, and the remaining images are loaded. This discard is a carryover from analyses on initial datasets where these slices tended to contain artifacts and increased scatter due to proximity to the MicroCT system collimator.

For each subset, the Matlab software segments frame by frame, using a thresholding method for each frame with the full-frame mean as the thresholding value, followed by a morphological opening on the resulting mask to reduce spot noise, using a disk-shaped kernel of radius 10.

The resulting mask is then run through an iterative procedure of mask dilation using a disk-shaped kernel of radius 10 followed by half-mean thresholding within the mask area until convergence is reached. This threshold tends to be much stricter than the previous frame mean threshold due to the concentration of high value pixels used. The resulting mask is filled to include any void areas using a flood fill operation where any empty pixels within the outer boundary of the mask area are included in the mask, completing the segmentation process.

If a metal safety cage is present as in TSL MicroCT data, an additional step is taken to remove the cage: the filled mask undergoes morphological erosion with a disk structural element of radius approximately equal to the thickness of the cage (radius 8). The intersection of this filled mask with the unfilled mask represents the specimen container without the safety cage, and this mask is filled and used.

Reference materials are subsequently identified within the reference mask by numbering each distinct mask region, computing the angular position of each centroid, and using the largest angular gap between successive centroid values to identify material label ordering according to carousel specifications. In the coordinate system used, the center of the image is considered the origin, and angular values are in radians relative to the positive x-axis (directly to the right of the origin). At "high energy" (Exp1 as defined in section 5.1), expected attenuation values for the materials are ordered from highest to lowest as: aluminum, Teflon, graphite, Delrin, water, and ethanol. At "low energy" (Exp2 as defined in section 5.1), attenuation values are ordered as: aluminum, Teflon, Delrin, graphite, water, and ethanol. Note that the relative ordering of the Delrin and graphite reference materials changes with the source energy used. This ordering can be used to check that the segmentation region labels are correct.

The voxels resulting from the segmentation process are written to two separate files. The first is a Matlab data file of the form *raw_material.mat*, containing one three dimensional matrix representing the mask and a second representing the segmented voxels. The second is *material.txt*, in an ASCII format with one line per voxel, including x-position, y-position, z-position, and voxel value, in that order. Position values are integer-valued, while voxel values may be integer- or floating-point valued (non-normalized). This ASCII text file is space delimited, and is fully compatible with Jeff Kallman's **Eroder** and **SimTest** Java-based analysis software (see [6]).

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

2. Erosion

The erosion process first loads in the results of the segmentation from the appropriate .mat files, and then performs a pre-erosion for any specimen or reference enclosed within a container. At the current time the erosion values corresponding to the specimen, and the water and ethanol reference material containers is hard-coded at radius 8 for the specimen container, and radius 10 for water and ethanol containers.

After any necessary pre-erosion, the resulting mask then undergoes morphological erosion with a disk element of the radius which most closely preserves ~80% erosion of mask voxels within the frame. The current implementation of the code starts with a disk of radius 1 as the erosion kernel, and iterates through integer values of radius until the radius that most closely preserves approximately 80% of the starting mask is found. After erosion, this internal 80% area is used for statistical computation.

Upon erosion, all eroded data from a single test folder is normalized by scaling with a scalar factor obtained from setting the mean value of eroded voxels from the reference material in Exp1 to its specified standard value. The current standard is to set water in Exp1 to 1000.

The voxels resulting from the erosion process are written to two separate files. The first is a Matlab data file of the form *erode_material.mat*, containing one three dimensional matrix representing the mask and a second representing the eroded voxels. The second is *material_core.txt*, in an ASCII format with one line per voxel, including x-position, y-position, z-position, and voxel value, in that order. Position values are integer valued, while voxel values may be integer or floating point valued. This ASCII text file is space delimited, and is fully compatible with Jeff Kallman's **SimTest** analysis software.

3. KDE Estimation

The MicroCT GUI uses the following KDE computation formulae:

$$KDE(x) = \frac{1}{nh} \sum_{i=1}^{n} K\left(\frac{x - x_i}{h}\right), \text{ where}$$

$$K\left(\frac{x - x_i}{h}\right) = \frac{1}{\sqrt{2\pi}} \exp\left(\frac{(x - x_i)^2}{2h^2}\right), h = 0.9 A n^{-0.2}, A = \min(\sigma_x, IQR(x))$$

In this computation, **x** represents attenuation values at which the KDE is computed, **x_i** represents individual voxel values, **n** represents the voxel count, **σ_x** is the variance of the voxel values, and **IQR** is the inter-quartile range of the voxel values, defined as the difference between the values of the first and third quartile. A quartile is one of three points dividing a data set into four equal groups. The first quartile cuts off the lowest 25% of data, while the third quartile cuts off the highest 25% of data. The second quartile is the median. The exact process by which the IQR is obtained is as follows:

1. Compute the median by sorting the elements of the set in numerical order and finding the central element. If no exact central element is found (if the set has even parity), take the average of the center-most two elements. Using this median value, divide the dataset into two equal halves, one set of values appearing before the median point in the ordered set, and one set of values appearing after the median point in the ordered set.

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

2. If the number of elements in the total set is even, compute the median for each half, where Q1 is the median of the lower half and Q3 is the median of the upper half. Then, IQR = Q3 – Q1.

3. If the number of elements in the set is odd, perform step 2 including the middle element of the whole set in each subset to obtain $Q1_1$ and $Q3_1$. Perform step 2 excluding the median element from each set to obtain $Q1_2$ and $Q3_2$. Then, IQR = ½($Q3_1$ – $Q1_1$) + ½($Q3_2$ – $Q1_2$).

For simplicity of running similarity comparisons across tests on saved data (such that KDEs do not need to be recomputed on a per-order basis), currently the GUI is set to compute KDE values indexed at the even integers of attenuation values on the LMHU scale.

The KDEs resulting from this computation are saved in the corresponding test directories at the destination directory location in files of the form *kde_material.mat*, containing the indexing attenuation values as well as the corresponding KDE values in Matlab array format.

4. Statistical Analysis

In generating the characterization Excel file, the GUI computes mean, differential entropy and variance for 1^{st} and 2^{nd} order eroded data from the specimen and references, and uses the ratios of low/high energy mean LACs (treated as domain) and known effective atomic mass ($^LZ_{eff}$) values (treated as range) to generate quadratic regression curves for low and high range $^LZ_{eff}$ estimation.

Differential entropy is approximated from the KDE with the following formula:

$$E = -\sum p \log(p), \text{ where } p(x) = KDE(x) * \Delta x$$

For estimating Z_{eff}, two quadratic regression curves are computed as follows:

1. Ethanol, Delrin and graphite have their LAC ratios and literature $^LZ_{eff}$ values combined into respective ordered pairs of the form (LAC ratio, $^LZ_{eff}$). These ordered pairs are used to generate a quadratic fit, as instructed by [5]. This is called the Low Range $^LZ_{eff}$ Fit curve, denoted as $f_L(x)$.

2. Delrin, aluminum, teflon and water have their LAC ratios and literature $^LZ_{eff}$ values combined into respective ordered pairs of the form (LAC ratio, $^LZ_{eff}$). These ordered pairs are used to generate a second quadratic fit, as instructed by [5]. This is called the High Range $^LZ_{eff}$ Fit curve, denoted as $f_H(x)$.

From these curves, an estimate for $^LZ_{eff}$ can be obtained by evaluating the appropriate $^LZ_{eff}$ value corresponding to the LAC ratio ($LACR_{spec}$) of the specimen, using the relationship between the specimen LAC ratio and Delrin's LAC ratio as a decision point between the two quadratic fits. Taking the specimen LAC ratio, if it is less than Delrin's LAC ratio, find the value of the low-range quadratic fit function $^LZ_{eff} = f_L(LACR_{spec})$. Otherwise, $^LZ_{eff} = f_H(LACR_{spec})$.

The statistical data are saved within the destination test directory, in a file of the form *test_name_characterization.xls*. They are also stored in struct format in the test directory, in a file named *analysis.mat*.

For document control purposes, user SHALL ensure that all working copies are identical to the Official Use Copy
posted at the designated ACEDPP project space on Livelink.

LLNL-TR-503292, Page 23 of 24

MicroCT: Semi-Automated Analysis of CT Reconstructed Data of Home Made
Explosive Materials Using the Matlab MicroCT Analysis GUI

IDD-MCT-SOP-008, Rev. 0
LLNL-TR-503292

Appendix D: Validation Testing

When first installed, the user should verify that the Automated MicroCT Analysis GUI is functioning properly. Included in the program package should be a .zip archive file, *validation_datasheets.zip*, which includes analysis output files from all test cases. **If any of the test cases' output from the Automated MicroCT Analysis GUI do not match, do not use this program and consult the point of contact at LLNL.**

The following is a table identifying all test cases, as well as the correct slice ranges to use for each case. In each test case, only run the Automated MicroCT Analysis GUI on test folders containing the appropriate recobj files. These files have been filtered to exclude frames with defects or artifacts in accordance with the requirements presented in sections 5.2.2 and 5.3 of this document.

Table 1. List of slices to use in each test for validation of software.

Test Case	Exp1 Slices	Exp2 Slices	Exp3 Slices	Exp4 Slices
091117_Priority13_Z4C2	Specimen: 28-38 Ref: 223-233	Specimen: 28-38 Ref: 223-233	Specimen: 28-38 Ref: 223-233	Specimen: 28-38 Ref: 223-233
091022_Priority13_Z1D1	Specimen: 53-63 Ref: 249-259	Specimen: 53-63 Ref: 249-259	Specimen: 53-63 Ref: 249-259	Specimen: 53-63 Ref: 249-259
091107_Priority13_Z5C2	Specimen: 28-38 Ref: 223-233	Specimen: 28-38 Ref: 223-233	Specimen: 28-38 Ref: 223-233	Specimen: 28-38 Ref: 223-233